

General Information

- Significant stable structure in highly acidic or alkali condition
- Low Free-PEG content
- Low Dioxane and Free-EO content

Physical Properties

Properties	Test Method	Unit	Specification
Molecular Weight	LC Method	-	2200 - 2600
Appearance (25 C)	Visual		Solid
Color (50 C)	ASTM D1209	APHA	100 Max
pH	ISO 4316	-	5.5 - 7.5
Hydroxyl Value	ASTM D4252	mgKOH/g	21.6 - 25.5
Water Contents	ASTM D1744	wt%	0.50 Max